

# CHARGEURS PCC

FASHION TECHNOLOGIES

LADIESWEAR · MENSWEAR · KIDSWEAR · PERFORMANCE · ECO-SOLUTIONS

## 110033

**CONSTRUCTION** Plain Weave  
**COMPOSITION** 100.0 % Polyester  
**COATING** Polyamide - 30 mesh  
**WEIGHT** 31.0 gr/m<sup>2</sup>  
**WIDTH** 150 cms  
**COLOURS** White , Natural , Black , Non Optical Black NBK , Non Optical White NOW , lava

### APPLICATION

Blouses  
Shirts  
Jackets - Blazers  
Pants  
Pants - Skirts  
Outerwear  
Waistbands

WOMENS AND MENS WEAR

### CARE INSTRUCTIONS



Washing



Chlorine



Ironing



Dry cleaning



Drying



Wet  
Cleaning

	Fusing Conditions	
 Glueline temperature	116/132 C	116/132 C
 Fusing pressure	2/3 gr/cm	2/4 bar
 Fusing time	12/15 s	12/15 s

In view of the wide variety of existing fabrics and other materials used by the clothing industry, Lainière de Picardie recommends that before industrial use, complete tests are carried out with the fabrics and other materials to be used, and on the machines that will be used. Lainière de Picardie guarantee is, explicitly limited to the replacement of any of its products recognised to be defective, to the exclusion of all other compensation or damages.



Class I



AMERICAS · EUROPE · MIDDLE EAST · AFRICA · ASIA PACIFIC

www.chargeurs-pcc.com