

CHARGEURS PCC

FASHION TECHNOLOGIES

LADIESWEAR · MENSWEAR · KIDSWEAR · PERFORMANCE · ECO-SOLUTIONS

KF501/25

CONSTRUCTION	Jersey
COMPOSITION	100.0 % Polyester
COATING	Polyamide - 25 mesh
WEIGHT	60.0 gr/m ²
WIDTH	150 cms
COLOURS	White , Natural , Non Optical White NOW , Non Optical Black NBK , Black
APPLICATION	Dresses Jackets - Blazers Pants Pants - Skirts Outerwear
WOMENS AND MENS WEAR	

CARE INSTRUCTIONS



Washing



Chlorine



Ironing



Dry cleaning



Drying



Wet
Cleaning

SMETA

	Fusing Conditions	
 Glueline temperature	116/138 C	116/138 C
 Fusing pressure	200/200 gr/cm	2/3 bar
 Fusing time	12/15 s	12/15 s

In view of the wide variety of existing fabrics and other materials used by the clothing industry, Lainière de Picardie recommends that before industrial use, complete tests are carried out with the fabrics and other materials to be used, and on the machines that will be used. Lainière de Picardie guarantee is, explicitly limited to the replacement of any of its products recognised to be defective, to the exclusion of all other compensation or damages.



Class I



AMERICAS · EUROPE · MIDDLE EAST · AFRICA · ASIA PACIFIC

www.chargeurs-pcc.com